

### PHYSICAL PROPERTIES & PACKAGING (FLOATING MULTILAYER MODULAR FLOORING - 8.5 MM / 0.5 MM)

USE	Commercial & Residential ( <i>Refer to Recommended Use PDF for Commercial Recommended Areas</i> )
SIZE	Multi-Width (3 Widths) 4.25 / 5.59 / 9.84 x 47.64 in. (108 / 142 / 250 x 1,210 mm)
THICKNESS - OVERALL	8.5 mm (0.335 in.)
THICKNESS - WEAR LAYER	0.5 mm (20 mil)
THICKNESS - LVT	2.0 mm (0.079 in.) Luxury Vinyl Tile (LVT)
CORE	5.0 mm (0.197 in.) ISOCORE Technology® (WPC)
PAD	1.5 mm (0.059 in.) IXPE with Ultra-Fresh
PROFILE	Micro-Bevel Edge
FINISH	FX3 Surface Protectant™ with Ultra-Fresh
COVERAGE - CARTON	9 (3 per Size) Pieces/Carton (19.5 Sq.Ft. / 1.82 Sq.M.)
COVERAGE - PALLET	60 Cartons/Pallet (1,172 Sq.Ft. / 108.9 Sq.M.)
COVERAGE - CONTAINER	16 Pallets/Container (18,755 Sq.Ft. / 1,742 Sq.M.)
LIMITED WARRANTY	15-Year Commercial / Lifetime Residential

### STANDARDS — MANUFACTURING & USAGE (ASTM F3261)

STANDARD	DESCRIPTION	REQUIREMENTS	RESULTS
ASTM F3261	Physical Characteristics / Tolerances	Refer to Standard	Passes Requirements <sup>1</sup>
ASTM F1914	Residual Indentation	Average: ≤ 0.007 in. (0.18 mm)	Passes Requirements
ASTM F1914	Surface Integrity	No Puncture Through Wear Layer / Décor Layer	Passes Requirements
ASTM F2199	Dimensional Stability	≤ 0.2% / lineal ft. (305 mm)	Passes Requirements
ASTM F2199	Curling	≤ 0.080 in. (2.0 mm)	Passes Requirements
ASTM F925	Chemical Resistance	No More Than "Slight Change"	Passes Requirements
ASTM F1514	Resistance to Heat	Average ΔE < 8.0	Passes Requirements
ASTM F1515	Resistance to Light	Average ΔE < 8.0	Passes Requirements
ASTM F970	Static Load	0.005 in., 250 psi	0.005 in., ≥ 500 psi

### STANDARDS — SAFETY & PERFORMANCE

STANDARD	DESCRIPTION	REQUIREMENTS	RESULTS
ASTM E648	Critical Radiant Flux (Radiant Panel)	Class I: ≥ 0.45 W/Sq. cm.	Passes Requirements <sup>2</sup>
ASTM E662	Smoke Density	Flaming & Non-Flaming ≤ 450	Passes Requirements <sup>3</sup>
CDPH Standard Method v1.2	VOCs/TVOCs, Formaldehyde	Refer to Standard	Passes Requirements
REACH SVHC 181	Substances of Very High Concern	Refer to Standard	Passes Requirements
ASTM F963	Heavy Metals	Refer to Standard (Table 1)	Passes Requirements
ASTM G21 <sup>4</sup>	Antifungal Activity	N/A (No Official Requirements)	Top: 0-1; Bottom: 0
CPSC-CH-C1001-09.3	Phthalates	Per CPSIA <sup>5</sup> ≤ 0.1% per Substance	Passes Requirements
ASTM D2047	Coefficient of Friction / Slip Resistance	N/A (No Official Requirements)	≥ 0.6 (Dry)
ASTM D4060	Abrasian Resistance	N/A (No Official Requirements)	Average: ≥ 25,000 cycles

### STANDARDS — SOUND

ASSEMBLY	ASTM E90	ASTM E492	ASTM E2179	RESULTS
6" Concrete Slab	STC 51	IIC 53	ΔIIC 24	Tested assemblies pass International Building Code (IBC) requirements of STC ≥ 50 and IIC ≥ 50 for multi-story dwellings
6" Concrete Slab + Drop-Ceiling	STC 62	IIC 69	Not Applicable	

### NOTES

- (1) ASTM F3261 - Physical Characteristics / Tolerances: includes Size, Squareness, Thickness, Wear Layer Thickness (Commercial Class), Flatness, Openings, and Ledging.
- (2) ASTM E648 - Critical Radiant Flux (Radiant Panel): Passes Requirements for Class I per International Building Code (IBC) 2018 & NFPA 101 Life Safety Code.
- (3) ASTM E662 - Smoke Density: 450 is the limit established by many state, county, and/or local building and/or fire codes, but is not set as a limit for (resilient) flooring products nationwide. Thus, Smoke Density requirements for flooring products may vary from jurisdiction to jurisdiction. Consult your building inspector / fire marshall to learn more.
- (4) ASTM G21 (Antifungal Activity): Top Surface (LVT Top Layer) scored 0-1 (no Growth to < 10% Growth); Bottom Surface (Underlayment) scored 0 (No Growth).
- (5) CPSIA = Consumer Product Safety Improvement Act.

Ultra-Fresh and the Ultra-Fresh logo are trademarks of Microban Products Company.