INCEPTION • RESERVE Waterproof SPC by METROFLOR"

CHEMICAL & STAIN RESISTANCE

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid (White Vinegar)	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Phenol	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
70% Isopropyl (Rubbing) Alcohol	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
Gasoline	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0
Sulfuric Acid	0	0	0	0	0	0

EXTENDED AGENT-LIST	5 MINUTES	24 HOURS

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	
A456 II Germicide	0	0	0	0	0	0	
Acetone	0	0	0	0	0	0	
Aniline Blue	0	0	0	0	0	0	
Ball Point Pen	0	0	0	0	0	0	
Betadine	0	0	0	0	0	0	
Bicarbonate	0	0	0	0	0	0	
Bleach 10%	0	0	0	0	0	0	
Blood	0	0	0	0	0	0	
Cherry Soda	0	0	0	0	0	0	
Disinfectants Phenolic/Quaternary	0	0	1	0	0	1	
Ecoshine Stainless Steel Polish	0	0	0	0	0	0	
Ethyl Alcohol	0	0	0	0	0	0	
Hematoxylin	0	0	2	0	0	2	
lodine	0	0	0	0	0	0	
Lemon Eze	0	0	0	0	0	0	
Lime A Way	0	0	0	0	0	0	
Methylene Blue	0	0	1	0	0	1	
Mineral Spirits	0	0	0	0	0	0	
Permanent Marker	0	0	0	0	0	0	
Potassium Permanganate	0	0	3	0	0	3	
Purell®	0	0	0	0	0	0	
QC 31 Neutral Cleaner	0	0	0	0	0	0	
QC 52 Glass Cleaner	0	0	0	0	0	0	
QC 53 General Purpose Cleaner	0	0	0	0	0	0	
Red Kool Aid	0	0	0	0	0	0	
Red Wine	0	0	0	0	0	0	
Shoe Polish Paste Brown	0	0	0	0	0	0	
Tar	0	0	0	0	0	0	
Yellow Mustard	0	0	0	0	0	0	

KEY

NOTES

Tests were conducted per ASTM F925 and values recorded after durations of 5 minutes and 24 hours. Testing and reporting were conducted by an independent laboratory (no affiliation with Metroflor Corporation).

0 - no change 1 - slight change 2 - moderate change 3 - severe change