

### PHYSICAL PROPERTIES & PACKAGING (FLOATING MULTILAYER MODULAR FLOORING - 5.2 MM / 0.5 MM)

USE	Commercial & Residential ( <i>Refer to Recommended Use PDF for Commercial Recommended Areas</i> )
SIZE	16 x 32 in. (406.4 x 812.8 mm)
THICKNESS - OVERALL	5.2 mm (0.205 in.)
THICKNESS - WEAR LAYER	0.5 mm (20 mil)
CORE	4.2 mm (0.165 in.) Solid Polymer Core (SPC)
PAD	1.0 mm (0.039 in.) HDPE
PROFILE	Grout Effect Edge
FINISH	FX2 Surface Protectant™
EMBOSS	Coral
COVERAGE - CARTON	7 Pieces/Carton (24.9 Sq.Ft. / 2.31 Sq.M.)
COVERAGE - PALLET	36 Cartons/Pallet (896 Sq.Ft. / 83.2 Sq.M.)
COVERAGE - CONTAINER	26 Pallets/Container (23,296 Sq.Ft. / 2,164 Sq.M.)
LIMITED WARRANTY	15-Year Commercial / Lifetime Residential

### STANDARDS — MANUFACTURING & USAGE (ASTM F3261)

STANDARD	DESCRIPTION	REQUIREMENTS	RESULTS
ASTM F3261	Physical Characteristics / Tolerances	Refer to Standard	Passes Requirements <sup>1</sup>
ASTM F1914	Residual Indentation	Average: $\leq 0.007$ in. (0.18 mm)	Passes Requirements
ASTM F1914	Surface Integrity	No Puncture Through Wear Layer / Décor Layer	Passes Requirements
ISO 23999	Dimensional Stability	$\leq 0.2\%$ / lineal ft. (305 mm)	Passes Requirements
ISO 23999	Curling	$\leq 0.080$ in. (2.0 mm)	Passes Requirements
ASTM F925	Chemical Resistance	No More Than "Slight Change"	Passes Requirements
ASTM F1514	Resistance to Heat	Average $\Delta E < 8.0$	Passes Requirements
ASTM F1515	Resistance to Light	Average $\Delta E < 8.0$	Passes Requirements
ASTM F970	Static Load	$\leq 0.005$ in. (0.13 mm), 250 psi	Passes Requirements

### STANDARDS — SAFETY & PERFORMANCE

STANDARD	DESCRIPTION	REQUIREMENTS	RESULTS
ASTM E648	Critical Radiant Flux (Radiant Panel)	Class I: $\geq 0.45$ W/Sq. cm.	Passes Requirements <sup>2</sup>
ASTM E662	Smoke Density	Flaming & Non-Flaming $\leq 450$	Passes Requirements <sup>3</sup>
CDPH Standard Method v1.2	VOCs/TVOCs, Formaldehyde	Refer to Standard	Passes Requirements
REACH SVHC 211	Substances of Very High Concern	Refer to Standard	Passes Requirements
ASTM F963	Heavy Metals	Refer to Standard (Table 1)	Passes Requirements
CPSC-CH-C1001-09.4	Phthalates	Per CPSIA <sup>4</sup> $\leq 0.1\%$ per Substance	Passes Requirements
ASTM D2047	Coefficient of Friction / Slip Resistance	N/A (No Official Requirements)	$\geq 0.6$ (Dry)
ANSI ESD STM97.2	Body Voltage	N/A (No Official Requirements)	Average (Abs): $\leq 2.0$ kV
ASTM D4060	Abrasian Resistance	N/A (No Official Requirements)	Average: $\geq 25,000$ cycles

### STANDARDS — SOUND

ASSEMBLY	ASTM E90	ASTM E492	ASTM E2179	RESULTS
6" Concrete Slab	STC 50	IIC 51	$\Delta$ IIC 25	Tested assemblies pass International Building Code (IBC) requirements of STC $\geq 50$ and IIC $\geq 50$ for multi-story dwellings
6" Concrete Slab + Drop-Ceiling	STC 62	IIC 65	Not Applicable	

### NOTES

- (1) ASTM F3261 - Physical Characteristics / Tolerances: includes Size, Squareness, Thickness, Wear Layer Thickness (Commercial Class), Flatness, Openings, and Ledging.
- (2) ASTM E648 - Critical Radiant Flux (Radiant Panel): Passes Requirements for Class I per International Building Code (IBC) 2018 & NFPA 101 Life Safety Code.
- (3) ASTM E662 - Smoke Density: 450 is the limit established by many state, county, and/or local building and/or fire codes, but is not set as a limit for (resilient) flooring products nationwide. Thus, Smoke Density requirements for flooring products may vary from jurisdiction to jurisdiction. Consult your building inspector / fire marshall to learn more.
- (4) CPSIA = Consumer Product Safety Improvement Act.